

Four new families of polynuclear Zn-Ln coordination clusters. Synthetic, topological, magnetic and luminescent aspects

Article (Accepted Version)

Griffiths, Kieran, Mayans, Julia, Shipman, Michael A, Tizzard, Graham J, Coles, Simon J, Blight, Barry A, Escuer, Albert and Kostakis, George E (2017) Four new families of polynuclear Zn-Ln coordination clusters. Synthetic, topological, magnetic and luminescent aspects. *Crystal Growth & Design*, 17 (4). pp. 1524-1538. ISSN 1528-7483

This version is available from Sussex Research Online: <http://sro.sussex.ac.uk/id/eprint/66844/>

This document is made available in accordance with publisher policies and may differ from the published version or from the version of record. If you wish to cite this item you are advised to consult the publisher's version. Please see the URL above for details on accessing the published version.

Copyright and reuse:

Sussex Research Online is a digital repository of the research output of the University.

Copyright and all moral rights to the version of the paper presented here belong to the individual author(s) and/or other copyright owners. To the extent reasonable and practicable, the material made available in SRO has been checked for eligibility before being made available.

Copies of full text items generally can be reproduced, displayed or performed and given to third parties in any format or medium for personal research or study, educational, or not-for-profit purposes without prior permission or charge, provided that the authors, title and full bibliographic details are credited, a hyperlink and/or URL is given for the original metadata page and the content is not changed in any way.

Four new families of polynuclear Zn-Ln coordination clusters. Synthetic, topological, magnetic and luminescent aspects.

Kieran Griffiths,^a Julia Mayans,^b Michael A. Shipman,^c Graham J. Tizzard,^d Simon J. Coles,^d Barry A. Blight,^c Albert Escuer,^b and George E Kostakis^{a,e}*

^a Department of Chemistry, School of Life Sciences, University of Sussex, Brighton BN1 9QJ, UK.

E-mail: G.Kostakis@sussex.ac.uk

^b Department de Química Inorgànica, i Orgànica, Secció Inorgànica and Institut de Nanociència i Nanotecnologia (IN²UB), Universitat de Barcelona, Martí Franqués 1-11, 08028 Barcelona, Spain.

^c School of Physical Sciences, University of Kent, Canterbury, CT2 7NH, UK.

^d EPSRC National Crystallography Service, School of Chemistry, University of Southampton, Highfield, Southampton SO17 1BJ, UK.

^e Science and Educational Center of Physics of Nonequilibrium Open Systems, Samara National Research University, Moskovskoye Shosse 34, Samara 443086, Russia.

RECEIVED DATE (to be automatically inserted after your manuscript is accepted if required according to the journal that you are submitting your paper to)

Running Title : Zinc - Lanthanide polynuclear Coordination Clusters

* Corresponding authors

ABSTRACT:

The employment of three structurally related Schiff bases H_2L1 , H_2L2 , and H_3L3 with zinc and lanthanide salts under various reaction conditions, gave four families of compounds formulated as $[Zn^{II}_2Ln^{III}_2(L1)_4(EtOH)_6][ClO_4]_2$ (**1-3**), $[Zn^{II}_5Ln(OH)(L1)_6(H_2O)]$ (**4-6**), $[Zn^{II}_4Ln^{III}_2(OH)_2(L2)_4(OAc)_2(NO_3)_2(DMF)_3].DMF$ (**7-9**), $[Zn^{II}_2Ln^{III}_2(L3)_2(NO_3)_2(CO_3)_2(CH_3OH)_2]$ (**10-12**) with robust and novel topologies. Synthetic aspects are discussed. A comprehensive topological analysis of all reported Zn^{II}/Ln^{III} CCs with a core nuclearity of four and above is presented and identifies that families (**4-6**) and (**7-9**) are the first examples of the **2,3,4M6-1** motif in Zn^{II}/Ln^{III} chemistry. Magnetic studies are presented for the Dy^{III} analogues (**1**, **7** and **10**) are presented, **7** demonstrates field-induced slow relaxation of the magnetization. Fluorescence studies are also discussed.


KEYWORDS : Coordination Clusters, Zinc, Lanthanide, Topology, Magnetism,

Introduction

In recent years, 3d-4f polynuclear Coordination Clusters (CCs) have attracted increasing interest as a result of their extraordinary and fascinating structural characteristics^{1–5} as well as their many potential applications in fields such as molecular magnetism,^{6–8} optical materials^{9–13} and catalysis.^{14–18} In particular, the first heteronuclear $\text{Zn}^{\text{II}} - \text{Eu}^{\text{III}}/\text{Sm}^{\text{III}}$ CCs were reported in 1995 by Brennan et al^{19,20}; more recent $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ examples followed.^{13,21,22} In 2009 Murugesu et al¹⁰ reported a multifunctional pentanuclear $\text{Zn}^{\text{II}}_2\text{Dy}^{\text{III}}_3$ CC exhibiting Single Molecule Magnet (SMM) and fluorescent properties. Since then the synthesis of $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ CCs has gained remarkable attention, this since to a) magnetic behaviour that can be explained due to the diamagnetic character of the Zn^{II} ion, which has also been shown to enhance the energy barrier in $\text{Zn}^{\text{II}}/\text{Dy}^{\text{III}}$ SMMs²³ and b) Eu^{III} and Tb^{III} are attractive luminescent centers, due to their long lived $^5\text{D}_0$ and $^5\text{D}_4$ excited states and the accompanying large Stokes' Shifts. In addition, the combination with Zn^{II} ions may produce species with enhanced luminescent properties via f–d energy transfer,²⁴ a plethora of such mixed metal species have been reported and the magnetic and luminescent properties of such compounds have been very well investigated.^{9,25–46}

Several organic ligands have been employed to build $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ CCs and Schiff Base ligands represent an ideal host to accommodate both elements and allow them to interact.^{27,35,47,48} The synthesis of the Schiff base ligand (*E*)-2-(2-hydroxy-3-methoxybenzylideneamino)phenol **H₂L1** (Scheme 1, left), was initially reported in 1971 and used to sequester UO_2 .⁴⁹ Since then, a number of 3d/4f compounds bearing this ligand have been reported.^{15,50–55} Recently, we employed **H₂L1** in $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ chemistry, to assemble a family of bimetallic tetranuclear CCs formulated as $[\text{Zn}_2\text{Ln}_2(\text{L1})_4(\text{NO}_3)_2(\text{DMF})_2] \cdot 2\text{DMF}$ (Ln is Sm, Eu, Tb, Gd, Dy and Yb) which promote Friedel Crafts^{17,56} and multicomponent catalysis.⁵⁷ An interesting feature of these molecules is the retention of their topology in solution, which further shows the importance of the rigidity of the ligands and allows some synthetic control over topology.

H₂L1 is particularly versatile and straightforward to synthesise, and readily modified to enhance the luminescent properties eg. by the introduction of chromophoric moieties such as naphthol, which are often employed to transfer absorbed energy efficiently to the lanthanide ions⁵⁸. We therefore used a systematic synthetic study using H₂L1 and its structurally related organic ligands H₂L2 and H₃L3 (Scheme 1, centercenter and right) in the synthesis of Zn^{II}/Ln^{III} CCs. This study is limited to the formation and characterization of the Dy^{III}, Tb^{III} and Eu^{III} derivatives which are expected to show interesting magnetic (Dy^{III}) and fluorescent (Tb^{III}/Eu^{III}) properties. Herein, we describe twelve new CCs formulated as [Zn^{II}₂Ln^{III}₂(L1)₄(EtOH)₆] 2(ClO₄) (**1-3**) where Ln is Dy^{III} (**1**), Tb^{III} (**2**) or Eu^{III}(**3**). [Zn^{II}₅Ln(OH)(L1)₆(H₂O)] (**4-6**) where Ln is Dy^{III} (**4**), Tb^{III} (**5**) or Eu^{III}(**6**). [Zn^{II}₄Ln^{III}₂(OH)₂(L2)₄ (OAc)₂(NO₃)₂(DMF)₃].DMF (**7-9**) where Ln is Dy^{III} (**7**), Tb^{III} (**8**) or Eu^{III} (**9**). [Zn^{II}₂Ln^{III}₂(L3)₂(CO₃)₂(NO₃)₂(CH₃OH)₂] (**10-12**) where Ln is Dy^{III} (**10**), Tb^{III} (**11**) and Eu^{III} (**12**). Magnetic studies of the dysprosium analogues are presented, as well as luminescent analyses in solution.



Scheme 1. Schiff Base ligands used in this study

EXPERIMENTAL SECTION

Materials. Chemicals (reagent grade) were purchased from Sigma Aldrich and Alfa Aesar. The synthesis and characterization of the HL ligand are described in the ESI. All experiments were performed under aerobic conditions using materials and solvents as received. *Safety note:* Perchlorate salts are potentially explosive; such compounds should be used in small quantities and handled with caution and utmost care at all times.

Instrumentation. IR spectra were recorded over the range of 4000-650 cm⁻¹ on a Perkin Elmer Spectrum One FT-IR spectrometer fitted with a UATR polarization accessory. ESI-MS data were

obtained on a VG Autospec Fissions instrument (EI at 70 eV). TGA analysis was performed on a TA Instruments Q-50 model (TA, Surrey, UK) under nitrogen and at a scan rate of 10 °C/min (University of Sussex). All steady-state UV-Vis absorbance measurements (University of Kent) were made by use of a Shimadzu UV-1800 UV-Vis Spectrophotometer in DMF as indicated with quartz cuvettes, while all steady-state solutions fluorescence emission measurements were carried out using a Cary Eclipse Fluorescence Spectrometer in either acetonitrile, or DMF as indicated with quartz cuvettes.

Magnetic studies. Variable-temperature magnetic studies were made by use of a MPMS-5 Quantum Design magnetometer operating at 0.03 T in the 300-2.0 K range. Magnetization measurements were made under a magnetic field range of 0 - 5 T. Diamagnetic corrections were applied to the observed paramagnetic susceptibility using Pascal's constants.

Ligand synthesis. The syntheses of $\text{H}_2\text{L1}^{59}$ and $\text{H}_2\text{L2}^{59}$ and $\text{H}_3\text{L3}^{60}$ were by the reported procedures.

Experimental

Preparation of Complexes

$[\text{Zn}^{\text{II}}\text{Ln}^{\text{III}}_2(\text{L1})_4(\text{EtOH})_4][\text{ClO}_4]_2$ (**1-3**) where Ln is Dy^{III} (**1**), Tb^{III} (**2**) or Eu^{III} (**3**). To a solution of $\text{H}_2\text{L1}$ (48.2 mg, 0.2 mmol) in EtOH (20 mL), $\text{Zn}(\text{ClO}_4)_2 \cdot 6\text{H}_2\text{O}$ (74 mg, 0.2 mmol) and $\text{Ln}(\text{OTf})_3$ (61 mg, 0.1 mmol) were added and the resultant solution was stirred for 5 minutes, Et_3N (62 μL , 0.45 mmol) was added and the mixture was stirred for a further 1h. The resulting cloudy yellow solution was filtered and allowed to stand at room temperature. After 4 days, small yellow crystals were obtained with yields in the range of 52% based on Zn. For **1**, CHN $[\text{Zn}^{\text{II}}\text{Dy}^{\text{III}}_2(\text{L1})_4(\text{EtOH})_6][\text{ClO}_4]_2$ observed: C-43.19%, H-4.06%, N-2.79%; expected: C-43.08%, H-4.26%, N-2.96%. for **2** CHN $[\text{Zn}^{\text{II}}\text{Tb}^{\text{III}}_2(\text{L1})_4(\text{EtOH})_6][\text{ClO}_4]_2$ observed: C-43.21%, H-4.44%, N-3.04%; expected: C-43.30%, H-4.28%, N-2.97%., for **3** CHN $[\text{Zn}^{\text{II}}\text{Eu}^{\text{III}}_2(\text{L1})_4(\text{EtOH})_6][\text{ClO}_4]_2$ observed: C-43.53%, H-4.26%, N-2.92%; expected: C-43.59%, H-4.31%, N-2.99%.,

$[\text{Zn}^{\text{II}}_5\text{Ln}(\text{L1})_6(\text{OH})(\text{H}_2\text{O})]$ (**4-6**) where Ln is Dy^{III} (**4**), Tb^{III} (**5**) and Eu^{III} (**6**). To a solution of H₂L1 (48.2 mg, 0.2 mmol) in MeCN (20 mL), LnCl₃.xH₂O (37 mg, 0.1 mmol) and ZnCl₂ (27.2 mg, 0.2 mmol) were added and the mixture was stirred for 5 minutes, Et₃N (62 μL, 0.45 mmol) was added and the mixture stirred for a further 1h. The resulting cloudy yellow solution was filtered and allowed to stand at room temperature. After 3 days, small yellow crystals were collected with yields in the range of 67% based on Zn. CHN (**4**) $[\text{Zn}^{\text{II}}_5\text{Dy}(\text{L1})_6(\text{OH})(\text{H}_2\text{O})]$ observed: C- 51.32%, H-3.41%, N-4.19%; expected C-51.29%, H-3.53%, N-4.27% , for **5** $[\text{Zn}^{\text{II}}_5\text{Tb}(\text{L1})_6(\text{OH})(\text{H}_2\text{O})]$ observed: C- 51.41%, H-3.50%, N-4.35%; expected C-51.29%, H-3.53%, N-4.27% , for **6** $[\text{Zn}^{\text{II}}_5\text{Eu}(\text{L1})_6(\text{OH})(\text{H}_2\text{O})]$ observed: C- 51.45%, H-3.60%, N-4.14%; expected C-51.58%, H-3.55%, N-4.29% ,.

$[\text{Zn}^{\text{II}}_4\text{Ln}^{\text{III}}_2(\text{OH})_2(\text{L2})_4(\text{OAc})_2(\text{NO}_3)_2(\text{DMF})_3].\text{DMF}$ (**7-9**) where Ln is Dy^{III} (**7**), Tb^{III} (**8**) or Eu^{III} (**9**). To a solution of H₂L2 (52 mg, 0.2 mmol) in DMF (10 mL), Ln(NO₃)₃.5H₂O (44 mg, 0.1 mmol), Zn(CH₃CO₂)₂.2H₂O (45 mg, 0.2 mmol) and Et₃N (62 μL, 0.45 mmol) were added and the solution was stirred for 1h. The clear yellow solution was filtered and underwent vapour diffusion with Et₂O. After 7 days, yellow needle-like crystals were obtained with yields of 44%. CHN $[\text{Zn}^{\text{II}}_4\text{Dy}^{\text{III}}_2(\text{OH})_2(\text{L2})_4(\text{OAc})_2(\text{NO}_3)_2(\text{DMF})_3].\text{DMF}$ observed: C-45.41%, H-3.86%, N-6.19%; expected C-45.59%, H- 3.83%, N-6.05%. for **5** $[\text{Zn}^{\text{II}}_4\text{Tb}^{\text{III}}_2(\text{OH})_2(\text{L2})_4(\text{OAc})_2(\text{NO}_3)_2(\text{DMF})_3].\text{DMF}$ observed: C-45.67%, H-3.79%, N-6.11%; expected C-45.79%, H- 3.85%, N-6.07%, for **6** $[\text{Zn}^{\text{II}}_4\text{Eu}^{\text{III}}_2(\text{OH})_2(\text{L2})_4(\text{OAc})_2(\text{NO}_3)_2(\text{DMF})_3].\text{DMF}$ observed: C-45.99%, H-3.90%, N-6.15%; expected C-46.03%, H- 3.86%, N-6.10%.

$[\text{Zn}^{\text{II}}_2\text{Ln}^{\text{III}}_2(\text{L3})_2(\text{CO}_3)_2(\text{NO}_3)_2(\text{CH}_3\text{OH})_2]$ (**10-12**) where Ln is Dy^{III} (**10**), Tb^{III} (**11**) and Eu^{III} (**12**). To a solution of H₃L3 (71.6 mg, 0.1 mmol) in MeOH (20 mL), Et₃N (61.5 μL, 0.45 mmol) was added and the solution was stirred for 10 min. Ln(NO₃)₃.5H₂O (44 mg, 0.1 mmol) and Zn(NO₃)₂.6H₂O (58 mg, 0.2 mmol) were added and the resultant solution was stirred for a further 40min. The clear yellow solution was filtered and left to stand at room temperature. After 5 days, small yellow crystals were obtained with a yield of 80 % based on Zn. CHN (**10**) $[\text{Zn}^{\text{II}}_2\text{Dy}^{\text{III}}_2(\text{L3})_2(\text{CO}_3)_2(\text{NO}_3)_2(\text{CH}_3\text{OH})_2]$

observed C-34.89%, H-3.16%; N-5.88%; expected C-34.95%,H-3.21%,N-5.83%. for **11** $[\text{Zn}^{\text{II}}_2\text{Tb}^{\text{III}}_2(\text{L3})_2(\text{CO}_3)_2(\text{NO}_3)_2(\text{CH}_3\text{OH})_2]$ observed C-35.21%, H-3.34%; N-5.81%; expected C-35.19%, H-3.23%, N-5.86%. for **12** $[\text{Zn}^{\text{II}}_2\text{Eu}^{\text{III}}_2(\text{L3})_2(\text{CO}_3)_2(\text{NO}_3)_2(\text{CH}_3\text{OH})_2]$ observed C-34.55%, H-3.24%; N-5.89%; expected C-35.49%,H-3.26%,N-5.91%.

X-ray Crystallography. Data and unit cells (Tables S1-S4) for **1-6**, **10**, **11** and **12** (ω - scans) were obtained at the University of Sussex by use of an Agilent Xcalibur Eos Gemini Ultra diffractometer with CCD plate detector under a flow of nitrogen gas at 173(2) K using Mo K α radiation ($\lambda = 0.71073$ Å). CRYSLIS CCD and RED software was used respectively for data collection and processing. Reflection intensities were corrected for absorption by the multi-scan method. Data for **7**, **8**, **9**, **13** and **14** were collected at the National Crystallography Service, University of Southampton⁶¹ on a Rigaku CrystalClear, processed with CrysAlisPro and solved by intrinsic phasing methods with SHELXT⁶². All crystal structures were then refined on Fo2 by full-matrix least-squares refinements using SHELXL.⁶² All non-H atoms were refined with anisotropic thermal parameters, and H-atoms were introduced at calculated positions and allowed to ride on their carrier atoms. Structures **7**, **8** and **9** are isostructural with a large solvent channel parallel to the b-axis present in each structure. From the difference map a large peak of electron density is present in each of these structures which has proved impossible to assign in a chemically sensible manner. For each of these structures we performed the elemental and TGA analysis three times for each sample and obtained the expected results at all times. The absence of Cl was confirmed by ICP analysis. Additionally, data were collected at 30K for **9** in an attempt to better characterize the structure within the solvent channel but this was unsuccessful. The electron contribution from this large peak along with that of the diffuse solvent has been taken into account using the SMTBX solvent masking as implemented in Olex2. Geometric/crystallographic calculations were performed using PLATON,⁶³ Olex2,⁶⁴ and WINGX⁶⁵ packages; graphics were prepared with Crystal Maker.⁶⁶ Crystallographic details are given in Tables S1-S4. CCDC 1505845-1505854


RESULTS AND DISCUSSION

Synthetic issues. It is well-known that the stoichiometric ratio, metal salt, temperature, atmosphere, solvent, time of reaction, can all affect the nature of the final product. The semi-rigid **H₂L1** ligand has two pockets-I(ONO) and –II(ONO) (Scheme 1, left) which are suitable for binding both 3d and 4f metal ions. The reaction between, Dy(OTf)₃, Zn(ClO₄)₂ and **H₂L1** in the presence of base (Et₃N) in EtOH in the molar ratio 1:2:2:4.5, afforded yellow needle like crystals of **1** in a tolerable yield (57%) after 1 week. The reactions with similar ratios but different counter anions and solvent yielded the recently reported isoskeletal⁵⁹ CCs formulated as [Zn₂Ln₂(**L1**)₄(NO₃)₂(DMF)₂].¹⁷ Aiming to synthesize the isoskeletal tetranuclear zinc analogue of [Ni₂Ln₂(**L1**)₄Cl₂(CH₃CN)₂],¹⁵ we performed the reaction with similar ratios in MeCN with DyCl₃ and ZnCl₂ that yielded after 2 weeks jagged crystals of **4** possessing a topology unseen in the literature for these metals. A modified form of this ligand (E)-3-((2-hydroxy-3-methoxybenzylidene)amino)naphthalen-2-ol (**H₂L2**, Scheme 1 middle) that offers similar pockets to **H₂L1** has been employed to act as a sensitizer to enhance luminescence of the resulting complexes. The same molar reactant ratios in DMF, with Dy(NO₃)₃ and Zn(OAc)₂., After 1 week of vapour diffusion with Et₂O, large yellow plate like crystals of **7** were afforded in a good yield (70%). With the retention of the o-vanillin unit and replacement of the aminophenol by 1,3-diamino-2-propanol the ligand **H₃L3** (Scheme 1, right), offering similar pockets to that in **H₂L1** and **H₂L2** and one extra pocket was obtained. The use of **H₃L3** for the first time in Zn^{II}/Ln^{III} chemistry, gave the tetranuclear compounds **10 – 12**. A summary of these synthetic procedures is shown in **Table 1** and **Scheme 2**.

Table 1. Synthetic Strategies of preparing Zn^{II}/Ln^{III} CCs.

Ratio ^a	Ligand	Ln source	Zn source	Crystallisation method/ time(days)	Solvent	Compound
A:B:C:D = 1:2:2:4.5	H ₂ L1	Ln(OTf) ₃	Zn(ClO ₄) ₂ ·6H ₂ O	SE / 7	EtOH	Zn ₂ Ln ₂ (1,2,3)
A:B:C:D = 1:2:2:4.5	H ₂ L1	Ln(NO ₃) ₃ ·5H ₂ O	Zn(NO ₃) ₂ ·6H ₂ O	VD Et ₂ O / 9	DMF	Zn ₂ Ln ₂ ¹⁷
A:B:C:D = 1:2:2:4.5	H ₂ L1	LnCl ₃ ·xH ₂ O	ZnCl ₂	SE / 3	MeCN	Zn ₅ Ln (4,5,6)
A:B:C:D = 1:2:2:4.5	H ₂ L2	Ln(NO ₃) ₃ ·5H ₂ O	Zn(CH ₃ CO ₂) ₂ ·2H ₂ O	VD Et ₂ O / 7	DMF	Zn ₄ Dy ₂ (7,8,9)
A:B:C:D = 1:2:2:4.5	H ₃ L3	Ln(NO ₃) ₃ ·xH ₂ O	Zn(NO ₃) ₂ ·6H ₂ O	SE / 5	MeOH	Zn ₂ Ln ₂ (10,11,12)

(a) A= Dy^{III} salt, B = Zn^{II} salt, C= H_xLY, D = Et₃N



Scheme 2. Synthetic scheme for the preparation of (**1-12**)

Crystal Structure Description. Compounds **1** – **3** crystallize in the monoclinic $P21/n$ space group and are isoskeletal, thus only **1** will be described. The asymmetric unit of **1** contains one Zn^{II} ion; one Dy^{III} ion; two doubly deprotonated organic ligands (**L1**); three coordinated ethanol molecules; one to the Zn^{II} and the other two to the Dy^{III} ion; one perchlorate and one ethanol molecule. The main core of **1** can be described as defect dicubane⁶⁷ and is isoskeletal to the previous reported Ni_2Ln_2 ,^{15,50} and Co_2Ln_2 ^{15,51} cores. The organic ligands exhibit two different coordination modes (modes I and II, Scheme 2). In the first mode (mode I, Scheme 2), the two phenoxide oxygen atoms and the imine nitrogen atom are chelated to the Zn^{II} center, and the two phenoxide atoms are further bonded to two Dy^{III} ions ($\text{Dy}(1)$ and its symmetry related) and the methoxide oxygen atoms is and bound to $\text{Dy}(1)$. In the second mode (mode II, Scheme 2), the two phenoxide oxygen atoms and the imine nitrogen atom are chelated to the Dy^{III} center, while the phenoxide oxygen atom (from the 2-aminophenol unit), is further bound to two Zn^{II} centers. One ethanol molecules is bound one to the Zn^{II} ion and two others are bound to the Dy^{III} ion. Each Zn^{II} center coordinates to six atoms (O_5N) and displays an octahedral coordination, while each Dy^{III} center coordinates to eight atoms (O_7N). Using Shape software,⁶⁸ the geometry of $\text{Dy}(1)$ can be best described as biaugmented trigonal prismatic, with an $S(\text{P})$ value 1.415. There are two $\text{Zn}^{\text{II}}\cdots\text{Dy}^{\text{III}}$ distances at 3.5513(5)Å and 3.5329(5) Å and one $\text{Zn}^{\text{II}}\cdots\text{Zn}^{\text{II}}$ distance at 3.172(5)Å. Two coordinating ethanol molecules, one to Zn^{II} and one to Dy^{III} ion, form an H-bond ($\text{O8} - \text{H8}\cdots\text{O9}$) while the third coordinating ethanol molecule forms an H-bond with the lattice EtOH ($\text{O7} - \text{H7}\cdots\text{O10}$), which in turn is H-bonded to the uncoordinated methoxide oxygen atom ($\text{O10} - \text{H10A}\cdots \text{O1}$) (Fig S1). No other intramolecular interactions (e.g H-bonds or stacking) can be found between neighbouring entities. According to our topological representation,^{69,70} the main core of compound **1** can be described as **2,3M4-1**⁷⁰ and according to a literature survey⁷¹ this topology can be found in Zn_2Eu_2 ¹⁹ and Zn_2Yb_2 ⁷² CCs and the recent examples reported by us.¹⁷






Figure 1. The structure of compound **1** (up) and its core (down). C, H atoms and lattice molecules are omitted for clarity. Colour code Zn (grey), Dy (light blue), O (red), N (blue).



Scheme 3. The coordination modes found in **1** and **4**.

Compounds **4** – **6** crystallize in the triclinic *P*-1 space group and are isoskeletal, thus only **4** will be further described. The asymmetric unit of **1** contains five Zn^{II} ions, one Dy^{III} ion, six doubly deprotonated organic ligands (**L1**), one triply bridging hydroxyl group, one coordinated water molecule and two lattice molecules (one water and one acetonitrile). The main core of **1** can be considered as four fused triangles forming a distorted “chair” shaped core. The five Zn^{II} ions are situated in plane, while the Dy^{III} is situated 1.998 Å above this plane. Each of the six organic ligands is chelated to one metal center and further bridges other metal centers with the phenoxide and methoxide oxygen atoms. Three different coordination modes can be found for the six organic ligands; 3, 1 and 2 for modes I, II and III, respectively (Scheme 3). The hydroxyl group bridges Zn2, Zn3 and Dy1 and is situated (0.311 Å) above their plane. The coordination sphere of Zn3 is completed by one water molecule. Zn1 and Zn5 are five coordinated (O₄N) with trigonality index $\tau = 0.79$ and 0.88 , respectively, indicating that they adopt distorted trigonal bipyramidal coordination. Zn2 and Zn3 are five coordinated (O₄N) with trigonality index $\tau = 0.46$ and 0.43 , respectively, indicating that the coordination is between square pyramidal and trigonal bipyramidal.⁷³ Zn4 is six coordinated (O₅N). From Shape software,⁶⁸ the geometry of Zn4 can be best described as trigonal prismatic, with S(P) value 5.126. The Dy^{III} center coordinates to nine atoms (O₈N). From Shape software,⁶⁸ the coordination of Dy(1) can be best described as between a spherical tricapped trigonal prism and a spherical capped square antiprism [S(P) 1.606 and 1.656, respectively]. There are two Zn^{II}...Dy^{III} distances of 3.4317(3) Å and 3.4452(3) Å and four Zn^{II}...Zn^{II} distances at 3.0942(3) Å, 3.1296(3) Å, 3.527(3) Å and 3.626(3) Å. The coordinating water molecule forms two strong H-bonds, one with the methoxido oxygen atom (O7...O1AA) and the other with lattice water (O7...O3A). No other

supramolecular interactions (H-bonds or stacking) can be found between neighbouring entities. According to our topological representation,^{69,70} the main core of compound **4** can be described as **2,3,4M6-1**⁷⁰ and represents the first example of this configuration in Zn^{II}/Dy^{III} chemistry.








Figure 2. The structure of compound **4** (upper) and its core (middle). C, H atoms and lattice molecules are omitted for clarity. Colour code Zn (grey), Dy (light blue), O (red), N (blue), (Lower) The decorated **2,3,4M6-1** motif.

Compounds **7–9** crystallize in the monoclinic $P2_1/c$ space group and are isoskeletal, thus only **7** will be further described. The asymmetric unit of **7** contains four Zn^{II} ions, two Dy^{III} ions, four doubly deprotonated organic ligands (**L2**), two triply bridging hydroxyl groups, two acetates, three coordinating and one lattice DMF molecules. One of the coordination sites of Dy is disordered with water and nitrate present. The core of **7** can be considered as four fused triangles. Dy2, Zn1, Zn2 and Zn3 are strictly coplanar, while Dy1, Zn4, Zn3 and Zn2 are nearly so. The distorted angle between the two mean planes is 62.39° . Alternatively, the core can be considered as a Zn^{II}_4 defect dicubane with each Dy^{III} ion attached in the wings. Each organic ligand is chelated to one Zn^{II} ion forming four neutral metalloligands (ZnL2) which are further bridged to neighbouring Zn^{II} and two Dy^{III} ions. In total each **L2** coordinates to three metal centers; two Zn^{II} and one Dy^{III} , exhibiting a coordination mode analogous to mode I (Scheme 3). Each hydroxyl group bridges three metal centers, O1 bridges Dy1, Zn2 and Zn4, and O2 bridges Dy2, Zn1 and Zn3, and O1 and O2 are 0.895 and 0.911 Å, respectively above the plane. Each acetate group bridges two metal centers, Dy1 – Zn4 and Dy2, Zn1.

Two DMF molecules coordinate to Dy1 and one N,N' – DMF and one nitrate complete the coordination geometry of Dy2. Each Zn^{II} ion has coordination number six (O₅N) albeit with a distorted octahedral coordination geometry. Each Dy^{III} ion coordinates to eight oxygen atoms. From Shape software,⁶⁸ the geometry of Dy(1) and Dy(2) can be best described as between biaugmented trigonal prismatic and triangular dodecahedral [S(P) values 1.763 and 1.868, respectively] and biaugmented trigonal prism [S(P) value 1.626], respectively. There are four Zn^{II}...Dy^{III} distances between 3.3598(10) Å - 3.5333(10) Å and four Zn^{II}... Zn^{II} distances 3.1216(12) Å - 3.354(12) Å. The lattice N,N' – DMF molecule forms strong H-bonds with the two hydroxyl groups. No other supramolecular interactions (H-bonds or stacking) can be found between neighbouring entities. According to our topological representation,^{69,70} the core of compound **7**, like the core of **4**, can be described as **2,3,4M6-1**⁷⁰. A literature survey reveals that the same motif with the same M/Ln ratio can be seen in Ni/Ln⁵² and Co/Ln⁷⁴ chemistry.







Figure 3. The structure of compound **7** (upper) and its core (middle). C, H atoms and lattice molecules are omitted for clarity. Colour code Zn (grey), Dy (light blue), O (red), N (blue), (Lower) The decorated **2,3,4M6-1** motif.

Compounds **10** – **12** are tetranuclear CCs synthesized from a mixture with a 2:1:1:4.5 Zn / Dy / ligand / base ratio in MeOH as solvent. All compounds crystallized in the monoclinic $P2_1/n$ space group and are isoskeletal, thus only **10** is further described. The asymmetric unit contains one Zn^{II} ion, one Dy^{III} ion, one doubly deprotonated organic ligand (**HL3**), one carbonate, one nitrate and one methanol molecule. The main core of **10** can be considered as two of Zn-Dy pairs bridged by two carbonate groups. The four metal centers are situated in a plane (Torsion angle Zn1 – Dy1 – Dy1 – Zn1 is 0). Each organic ligand is chelated to the Zn^{II} ion via the two imino N atoms and the two phenoxide O atoms and to the Dy^{III} ion via the two methoxido and two phenoxide O atoms (Scheme 3). The carbonate group bridges the two Dy^{III} ions via oxygen O3 and coordinates to Zn1 and the nitrate group is chelated to the Dy^{III} ion. The distorted octahedral geometry (O_4N_2) of the Zn^{II} ion is completed by the oxygen atom of a methanol molecule. The coordination number of the Dy^{III} ion is completed by one chelated nitrate. From Shape software,⁶⁸ the geometry of Dy(1) can be best

described as spherical capped square antiprism [S(P) 2.489]. There is one $\text{Zn}^{\text{II}} \cdots \text{Dy}^{\text{III}}$ distance at 3.446(2) Å and one $\text{Dy}^{\text{III}} \cdots \text{Dy}^{\text{III}}$ distance at 4.007(2) Å. The central OH group of the organic ligand remains protonated and forms a strong H-bond with an oxygen atom of a carbonate group of a neighbouring $\text{Zn}^{\text{II}}_2\text{Dy}^{\text{III}}_2$ entity forming a two dimensional (2D) H-bonded framework, which extends perpendicular to the *ac* plane. According to our topological representation,^{69,70} the main core of compound **10** can be described as **1,2M4-1**⁷⁰ and it is the fifth example of the motif in $\text{Zn}^{\text{II}}/\text{Dy}^{\text{III}}$ chemistry.^{32,34,39,41} A comparison between the $\text{H}_3\text{L3}$ ligand used for the synthesis of **10** and the Schiff base ligands used in the previous reported the same **1,2M4-1** motif indicates that, despite the existence of the central OH group, this type of ligand favours the formation of Zn-Ln^{27} dimers which combine via the carbonate unit to the tetranuclear motif.






Figure 4. The structure of compound **10** (upper) and its core (middle).. C, H atoms and lattice molecules are omitted for clarity. Colour code Zn (grey), Dy (light blue), O (red), N (blue). (lower) The 2D H-bonded framework seen in the crystal structure of **10**.

Magnetic Properties. Magnetic measurements were made on selected powdered samples of compounds **1**, **7** and **10** to detect any SMM response. In preliminary AC measurements at zero field and two frequencies (10 and 1000 G) the three compounds showed a similar response, which was only observable by the tail of their AC signals. A series of new measurements under fields up to 3000 G showed a shift of the signals to higher temperature but AC peaks were not observable for **1** and **10**, (Figure S9). In contrast, well defined peaks were obtained for **7** for frequencies larger than 80 Hz and under a field of 3000 G, Figure S10. These measurements are evidence of strong tunnelling relaxation. Complementary susceptibility measurements were made for **7**. The $\chi_M T$ product at room temperature is $27.2 \text{ cm}^3 \text{ mol}^{-1} \text{ K}$, slightly lower than the expected value of 28.3 for two Dy^{III} cations, (Figure 5, left). On cooling the $\chi_M T$ value decreases monotonically down to a final value of $20.7 \text{ cm}^3 \text{ mol}^{-1} \text{ K}$ at 2 K. Magnetization experiments show a fast increase of the magnetization and a roughly linear dependence with the applied field in the 2 - 5 T field range. The final value of $9.4 \text{ N} \mu_B$ (for the two

Dy^{III} cations) under the maximum explored field of 5 T is lower than the expected suggesting a moderately high anisotropy.




Figure 5. (left) $\chi_M T$ product vs. temperature for complex **7**. (right) AC susceptibility measurements for **7** at frequencies comprised between 23 and 1500 Hz.

The AC susceptibility measurement in the 80-1500 Hz frequency range show well defined frequency-dependent peaks. An Arrhenius fit of the maxima of the peaks for compound **7** gives an energy barrier of 10.2 cm⁻¹ and $\tau_0 = 7.1 \cdot 10^{-6}$, (Figure 5, right). In the light of the structural data it shows that the two Dy^{III} cations do not interact and are well isolated by the Zn₄ butterfly, compound **7** should be assumed as a Single-Ion-Magnet with a low barrier for the reversal of magnetization.

The magnitude of the barrier for systems of this kind is sensitive to multiple factors but the importance of the ligand field and the position of the charged or neutral donors around the lanthanide cation to determine the spatial arrangement of electronic density in the oblate-prolate model.^{75–77} For the case of Dy^{III} its oblate electron density will generate larger barriers when negatively charged donors are above and below the radial plane of the cation. For **7** we are far from this situation because the O-phenoxo and O-carboxylate donors (with the shorter Dy-O distances) are placed on the same side of the coordination sphere whereas the other side is occupied by solvent molecules with two Dy-O distances larger than 2.5 Å. Calculation of the direction of the easy axis for the Dy^{III} cations in low

symmetry environments, such as that in **7** can be performed with the MAGELLAN program.⁷⁸ The directions are similar, as can be expected from the similar (but not identical) coordination spheres around Dy1 and Dy2. The axes are directed towards the O-phenoxo donors and are inclined at 54.1° not parallel. Both factors in non-ideal arrangements of the charged O-donors around the Dy^{III} cations and the angle between the easy axes contribute to the low energy barrier of the system.




Figure 6. Relative position of the easy axis of the two Dy^{III} cations on the core of **7** (top) and in their DyO₈ coordination spheres (bottom). Red O-atoms corresponds to the O-phenoxo and O-carboxylate donors.

Photoluminescence. Solution luminescence measurements were made for nine of the CCs (**4-12**) in DMF and each of the three ligands (in MeCN). The spectra of the Dy^{III} containing species (Figure 7) show that broad ligand-based emission with some metal contribution (resulting in red-shift of the profile) dominates for each of the three compounds. Though each of these species have distinctly different absorption spectra, all three emit near 560 nm (**4**: $\lambda_{\text{em}} = 560$, **7**: $\lambda_{\text{em}} = 567$, and **10**: $\lambda_{\text{em}} = 555$) correlating with the $^4\text{F}_{9/2} - ^6\text{H}_{13/2}$ transition that accompanies Dy^{III} emission. However, the broad nature of these signals indicates the significance of the ligand contribution to these emitters. Compounds **4 - 9** containing **L1** and **L2** exhibited similar behaviour (see Figure S11). However, Tb and Eu-containing complexes with **L3** (Figure S12-S13) displayed more typical emission spectra for

lanthanide species with multiple narrow emission bands correlating to specific transitions within a broad ligand emission peak. In particular, **11** exhibits an emission spectrum centered at 550 nm comparable to that described by Murugesu and coworkers in 2009 with discrete $^5D_4 - ^7F_6$, $^5D_4 - ^7F_5$, $^5D_4 - ^7F_4$, $^5D_4 - ^7F_3$ transitions.¹⁰ Emission in the NIR region was not observed below 1100 nm for any of the nine compounds tested.





Figure 7. Normalised absorption (dashed line) and emission spectra (solid line) of compounds **4** (blue; $\lambda_{\text{ex}} = 440$), **7** (red; $\lambda_{\text{ex}} = 400$), and **10** (yellow; $\lambda_{\text{ex}} = 355$) recorded in DMF (1×10^{-5} M, 298 K).

Synthetic and Topological Aspects. Many polynuclear heterometallic $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ compounds have been reported in the literature, but a significant number of these are di or tri-nuclear species. There are fewer examples with a nuclearity greater than four, as above in Table 2 along with their core topology (**Figure 6**) and ligand (**Scheme 4**). Recently two $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ CC with nuclearity 30 were reported, showcasing the current interest in $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ chemistry.^{79,80} Adopting our topological approach, all compounds can be presented by the NDK-symbol (Table 2). The most common nuclearity reported of the $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ clusters is four; it shows a number of topologies, which appear to be dependent on the structure of the ligand used for their synthesis.

The most common $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ CC topology, share a common ligand structure (Scheme 4-top Left). The **1,2M4-1** topology is formed in alcoholic solvents (MeOH, EtOH) (**Table 2** entries 1,4,9, 31); Zn^{II} ions are co-ordinated between the imine/secondary amine and deprotonated hydroxyl groups, while Ln^{III} ions are bound to the deprotonated hydroxyl and methoxy groups, forming a $[\text{Zn}^{\text{II}}\text{Ln}^{\text{III}}(\text{L})]^{3-}$ unit. In these examples, counter-ions such as Cl or carbonate (from atmospheric CO_2) bridge between two $[\text{Zn}^{\text{II}}\text{Ln}^{\text{III}}(\text{L})]^{3-}$ units to form the **1,2M4-1** topology as a dimer. The coordination sphere is then completed by counter-ions such as NO_3 and solvent molecules for charge balance. Of the Schiff base ligands employed in polynuclear Zn/Ln CC synthesis, few demonstrate a nuclearity above five, tetranuclear compounds are the most frequently reported. This may be due to the many co-ordinating groups usually present and the ridged structural fragments. The **2,3M4-1** motif corresponding to a defect dicubane topology is very common motif in 3d/4f chemistry. We recently reported the first example of a family of Zn/Ln CCs that possess this motif,¹⁷ and in this work we report another variation of this topology. The second most widespread motif in hexanuclear 3d/4f chemistry is **2,3,4M6-1** (Figures 2&3 lower). According to a survey in CSD,⁷¹ 33 crystal structures^{52,54,81–89} possess this motif that corresponds to four fused triangles aligned in a plane or forming a twisted boat. The first 3d/4f CCs with this topology can be found in a family of $\text{Mn}_4^{\text{III}}\text{Ln}_2^{\text{III}}$ compounds where Ln is Gd, Tb, Y, reported in 2008 by Oshi et al.⁸¹ Other examples were reported in Mn/4f,^{54,82,83} Ni/4f,^{52,86} Co/4f,^{74,84,85,87} and Fe/4f⁸⁸ chemistry.

The **2,4M6-1** motif, in comparison to the previously discussed examples, is less common in 3d/4f chemistry. This motif is best described as a single central triangle with 3 triangles fused side on to each side. Overall this forms a larger triangle, which can be planar or distorted. The first example of this topology was a heterometallic $\text{Mn}^{\text{III}}_3\text{Li}^{\text{I}}_3$ cluster⁹⁰ reported in 1991, until recently only homometallic clusters e.g. $\text{Co}^{\text{II}}_3/\text{Co}^{\text{III}}_3$ ⁹¹ and Zn^{II}_6 ^{92,93} have been reported. There are three examples of 3d/4f CCs with the **2,4M6-1** motif exist in the literature $\text{Cr}^{\text{III}}_3\text{Ln}^{\text{III}}_3$ ⁹⁴, $\text{Co}^{\text{III}}_3\text{Ln}^{\text{III}}_3$ ⁹⁵ and $\text{Ni}^{\text{II}}_3\text{Ln}^{\text{III}}_3$ ⁹⁶ species. These examples show the same configuration of 3d and 4f ion nodes within the motif, with 4f ions occupying the vertices of the central triangle and 3d ions occupying the vertices of the larger

triangle resulting in a core of Ln^{III} ions. Compounds **7-9** are the first examples of the **2,4M6-1** motif in $\text{Zn}^{\text{II}}/\text{Ln}^{\text{III}}$ chemistry. In the present study, despite using organic ligands that offer similar pockets, a range of topologies was obtained and the unexpected involvement of the non-expected formed carbonate group, does not allow for a complete systematic study.



Scheme 4. The organic ligands used in the synthesis of Zn/Ln CCs.

Table 2. Reported Polynuclear Zn^{II}/Ln^{III} species with a nuclearity of 4 and above.

Entries	Complexes	Ligand	Nuclearity	Nuclearity	Topological Nomenclature	Reference
1	[Nd ₂ (Zn L5) ₂ Cl ₆ (MeOH) ₂]·MeOH [Dy ₂ Zn ₂ (L6) ₂ (OAc) ₂ (CO ₃) ₂]·10CH ₃ OH	H ₂ L5 H ₂ L6	Zn ₂ Ln ₂	4	1,2M4-1	^{34, 47}
2	[Zn ₂ Ln ₃ (L4) ₃ (N ₃) ₅ (OH) ₂] Ln = (Tb, Eu, Ho, Dy)	H ₂ L4	Zn ₂ Ln ₃	5	1,2,3M5-1	10
3	[Zn ₂ (L6) ₃ Cl ₂ (OH) ₃ Ln ₃ (N ₃) ₂]; Ln=(La, Nd, Yb, Er)	H ₂ L6	Zn ₂ Ln ₃	5	1,2,3M5-1	⁹⁷
4	[Zn ^{II} ₂ Ln ^{III} ₂ (L7) ₂ (CO ₃) ₂ (NO ₃) ₂].solv Ln = Dy, Tb, Gd	H ₂ L7	Zn ₂ Ln ₂	4	1,2M4-1	³⁹
5	[Zn ^{II} ₂ Ln ^{III} ₂ (L8) ₂ (CO ₃) ₂ (NO ₃) ₂].solv Ln = Dy, Tb, Gd	H ₂ L8	Zn ₂ Ln ₂	4	1,2M4-1	³⁹
6	[Zn ₂ Yb ₂ (L6) ₂ (l-OH) ₂ Cl ₄]·2MeCN	H ₂ L9	Zn ₂ Ln ₂	4	1,2M4-1	⁹⁸
7	[Zn ₈ Ln ₄ (L10) ₂ (OAc) ₂₀ (OH) ₄] Ln= Nd, Yb	H ₂ L10	Zn ₈ Ln ₄	12	2(1,2,3M6-1)	⁹⁹
8	[Zn ₄ Eu ₄ (L11) ₄ (CO ₃) ₆]·EtOH	H ₂ L11	Zn ₄ Ln ₄	8	1,3M8-1	³⁵
9	[Zn ^{II} ₂ Eu ^{III} ₂ (PhCOO) ₂ (L12) ₄] [Zn ^{II} ₂ Dy ^{III} ₂ (PhCOO) ₂ (L12) ₄] [Zn ^{II} ₂ Tb ^{III} ₂ (PhCOO) ₂ (L12) ₄]	H ₂ L12	Zn ₂ Ln ₂	4	2M4-1	^{100, 25, 101}
10	Zn ₂ Dy ₂ (L12) ₂ (μ ₃ -OH) ₂ (μ ₄ -OH)(dbm) ₂ (MeOH) ₂]X (X = NO ₃ , ClO ₄)	H ₂ L12	Zn ₂ Ln ₂	4	3M4-1	⁴⁰
11	[Zn ^{II} ₂ Ln ^{III} ₂ (L13) ₂ (CO ₃) ₂ (NO ₃) ₂].4C H ₃ OH Ln = Gd, Yb	H ₂ L13	Zn ₂ Ln ₂	4	1,2M4-1	³²
12	[(Yb L14) ₂ (H ₂ O)Cl(Oac)] ₂ ·[ZnCl ₄] ₂	H L14	Zn ₂ Ln ₂	4	3M4-1	¹⁰²
13	[Zn ₂ Ln ₂ (OH) ₂ (L15) ₂ (OAc) ₅ (EtOH)(H ₂ O)](ClO ₄)·2EtOH·1.5H ₂ O Ln= Gd, Dy	H ₂ L15	Zn ₂ Ln ₂	4	3M4-1	³³
14	[Zn ₃ La(L19)(OAc) ₃]	H ₄ L19	Zn ₃ Ln	4	1,3M4-1	¹⁰³
15	[Zn ₃ La(L20)(OAc) ₃]	H ₄ L20	Zn ₃ Ln	4	1,3M4-1	¹⁰⁴
16	Zn ₃ La(L21)(NO ₃) ₃ (MeOH) ₂] / Zn ₃ La(L21) ₃ (NO ₃) ₂ (MeOH) ₆](NO ₃) .MeOH	H ₆ L21	Zn ₃ Ln	4	1,3M4-1	⁹³
17	Zn ₄ Dy(L17) ₄ (DMF) ₄ (NO ₃) ₃ Ln=Dy, Tb, Y, Er	H ₂ L17	Zn ₄ Ln	5	1,4M5-1	³⁸
18	Zn ₁₆ Ln(L17) ₁₆ (Py) ₈ (CF ₃ SO ₄) Ln= Tb, Dy, Yb, Er, Nd	H ₂ L17	Zn ₁₆ Ln	17	2,3,8M17-1	¹⁰⁵

19	$\text{Zn}_9\text{Ln}_2(\text{L17})_{10}(\text{OH})(\text{NO}_3)_{2.25}\text{Cl}_{0.75}; \text{Ln}=\text{Dy, Tb, Eu}$	H2L17	Zn_9Dy_2	11	1,1,2,2,5,7 M11-2	29
20	$[\text{Zn}_8\text{Ln}(\text{L16})_8(\text{OH})_3]; \text{Ln}=\text{Dy, Nd}$	H₂L16	Zn_8Ln	9	1,2,8M9-1	29
21	$[\text{Zn}^{\text{II}}_8\text{Gd}^{\text{III}}_4(\text{OH})_8(\text{L18})_8(\text{O}_2\text{CHMe}_2)_8](\text{ClO}_4)_4$	HL18	Zn_8Gd_4	12	3,6M12-1	42
22	$[\text{Zn}_2\text{Ln}_2(\text{L18})_4(\text{PhCO}_2)_5(\text{ROH})_2](\text{ClO}_4)(\text{MeOH})_2 \text{Ln}=\text{Dy, Gd}$	HL18	Zn_2Ln_2	4	3M4-1	36
23	$[\text{Zn}_6\text{Ln}(\text{OH})(\text{L22})_6(\text{NO}_3)_3](\text{OH})(\text{NO}_3)_2 \cdot 8\text{H}_2\text{O} \text{Ln}=\text{Er, Dy}$	HL22	Zn_6Ln	7	2,6M7-1	106
24	$[\text{Zn}_6\text{Dy}(\text{L23})_6(\text{OH})_3(\text{Oac})_3(\text{NO}_3)_3]$	HL23	Zn_6Ln	7	2,6M7-1	107
25	$[\text{Zn}_6\text{Ln}_{24}(\text{L24})_{24}(\text{Oac})_{22}(\mu_3\text{-OH})_{30}(\text{H}_2\text{O})_{14}](\text{ClO}_4)_7(\text{OAc}) \cdot 2\text{CH}_3\text{OH} \cdot 26\text{H}_2\text{O} \text{Ln}=\text{Gd, Tb, Dy}$	HL24	$\text{Zn}_6\text{Ln}_{24}$	30	3(3,3,5M10-1)	79
26	$[\text{Zn}^{\text{II}}_{12}\text{Dy}^{\text{III}}_{18}(\text{OH})_{30}(\text{L25})_{12}(\text{sal})_6(\text{OAc})_6(\text{NO}_3)_3(\text{H}_2\text{O})_6](\text{NO}_3)_3 \cdot 12\text{MeOH} \cdot 5\text{H}_2\text{O}$	H₂L25	$\text{Zn}_{12}\text{Ln}_{18}$	30	3,4,6,8M30-1	80
27	$[\text{Zn}_2\text{Ln}(\text{L26})_2(\text{Py})_2(\text{NO}_3)_2][\text{ZnLn}(\text{L})(\text{Py})(\text{NO}_3)_3(\text{H}_2\text{O})](\text{NO}_3)(\text{solv}) \text{Ln}=\text{Er, Gd}$	H₂L26	Zn_3Ln_2	5	(1,2M3-1)+(1M2-1)	108
28	$[(\text{THF})_8\text{Ln}_4\text{Se}(\text{L27})_8][\text{Zn}_8\text{Se}(\text{L27})_{16}]\cdot\text{THF} \text{Ln}=\text{Sm, Nd}$	L27	Zn_8Ln_4	12	(3,6M8-1)+(3M4-1)	109
29	$[\text{Zn}_4\text{Nd}_2(\text{L28})_4(1,4\text{-BDC})_2][\text{ZnNd}(\text{L28})(\text{NO}_3)_3(\text{OAc})]_2$	H₂L28	Zn_6Nd_4	10	2(1,2M3-1)+2(1M2-1)	110
30	$[\text{Zn}_2\text{Ln}_2(\text{L1})_4(\text{EtOH})_6] \cdot 2(\text{ClO}_4)$	H₂L1	Zn_2Ln_2	4	2,3M4-1	This work
31	$[\text{Zn}^{\text{II}}_5\text{Ln}(\text{OH})(\text{L1})_6(\text{H}_2\text{O})]$	H₂L1	Zn_5Ln	6	2,3,4M6-1	This work
32	$[\text{Zn}^{\text{II}}_4\text{Dy}^{\text{III}}_2(\text{OH})_2(\text{L2})_4(\text{OAc})_2(\text{NO}_3)_2(\text{DMF})_4]$	H₂L₂	Zn_4Ln_2	6	2,3,4M6-1	This work
33	$[\text{Zn}^{\text{II}}_2\text{Ln}^{\text{III}}_2(\text{L3})_2(\text{CO}_3)_2(\text{NO}_3)_2(\text{CH}_3\text{OH})_2]$	H₃L₃	Zn_2Ln_2	4	1,2M4-1	This work
34	$[\text{Zn}_2\text{Ln}_2(\text{L1})_4(\text{NO}_3)_2(\text{DMF})_2]$	H₂L1	Zn_2Ln_2	4	2,3M4-1	17




Figure 9. The topological representation of all known polynuclear Zn/Ln CCs

Conclusions

Reactions of zinc and lanthanide salts with various Schiff bases and a range of reaction conditions yielding four families of Zn/Ln CCs with robust and unseen topologies. Magnetic studies reveal the single ion magnet behavior of **7**, and luminescence studies indicate a significant ligand contribution to the emitters. Despite incorporating organic ligands, that offer similar coordination pockets, in similar synthetic ratios, products with a range of nuclearities, motifs are obtained, showing that more systematic studies are required to fully understand the growth of such crystalline species and target the specific products. However, these structural studies should be carried out in a careful manner. When we studied the reaction that yielded **4** under reflux instead of room temperature, two different type of crystals were observed $[\text{Zn}_4\text{Dy}_7(\text{OH})_4(\text{O}_2)_2(\text{L1})_8\text{Cl}_4(\text{H}_2\text{O})_4]\text{Cl}_5$ (**13**) and $[\text{Zn}_6\text{Dy}_4(\text{OH})_2(\text{L1})_{10}(\text{MeOH})_2(\text{H}_2\text{O})_4]\text{Cl}_2$ (**14**) and corresponding to **2,2,3,3M10-1** and **2,4,4,4M11-1** topologies, respectively (Fig S14). Our future studies will be focused as the following directions: a) to extend the synthetic study metal, ligand, co-ligands, ratios, aiming to obtain higher nuclearity Zn/Ln CCs and b) to test our ligand and coordination environment pockets selection in our topological approach to synthetic strategy.^{70,111}

Acknowledgements

We thank the EPSRC UK National Crystallography Service at the University of Southampton⁶¹ for the collection of the crystallographic data for compounds **7-9**, **13** and **14**. A. E. thanks for the support from Ministerio de Economía y Competitividad, Project CTQ2015-63614-P. We thank Dr. David Smith, for fruitful scientific discussions.

Supporting Information.

Crystal structures (cif files) and tables including structure refinement (Tables S1-S14) of compounds **1-12**.

Thermogravimetric analysis (TGA) of compounds **1-12** (Fig S1-S8).

Magnetic (Fig S9-S10) and luminescent (Fig S11-S13) measurements.

Synthesis and Characterisation of Ligands. (^1H , ^{13}C NMR)

ESI-MS of compounds **1** – **3**.

References

- (1) Papatriantafyllopoulou, C.; Moushi, E. E.; Christou, G.; Tasiopoulos, A. J. Filling the Gap between the Quantum and Classical Worlds of Nanoscale Magnetism: Giant Molecular Aggregates Based on Paramagnetic 3d Metal Ions. *Chem. Soc. Rev.* **2016**, *45*, 1597–1628 DOI: 10.1039/c5cs00590f.
- (2) Chen, W.-P.; Liao, P.-Q.; Yu, Y.; Zheng, Z.; Chen, X.-M.; Zheng, Y.-Z. A Mixed-Ligand Approach for a Gigantic and Hollow Heterometallic Cage {Ni₆₄ RE₉₆} for Gas Separation and Magnetic Cooling Applications. *Angew. Chem. Int. Ed.* **2016**, *55*, 9375–9379 DOI: 10.1002/anie.201603907.
- (3) Zhang, Z. M.; Pan, L. Y.; Lin, W. Q.; Leng, J. D.; Guo, F. S.; Chen, Y. C.; Liu, J. L.; Tong, M. L. Wheel-Shaped Nanoscale 3d-4f {CoII₁₆Ln_{III}₂₄} Clusters (Ln = Dy and Gd). *Chem. Commun.* **2013**, *49*, 8081–8083 DOI: 10.1039/c3cc45075a.
- (4) Kong, X.-J.; Ren, Y.-P.; Chen, W.-X.; Long, L.-S.; Zheng, Z.; Huang, R.-B.; Zheng, L.-S. A Four-Shell, Nesting Doll-like 3d-4f Cluster Containing 108 Metal Ions. *Angew. Chem. Int. Ed.* **2008**, *47*, 2398–2401 DOI: 10.1002/anie.200705731.
- (5) Kong, X.-J.; Long, L.-S.; Huang, R.-B.; Zheng, L.-S.; Harris, T. D.; Zheng, Z. A Four-Shell, 136-Metal 3d-4f Heterometallic Cluster Approximating a Rectangular Parallelepiped. *Chem. Commun.* **2009**, 4354–4356 DOI: 10.1039/b822609a.
- (6) Feltham, H. L. C.; Brooker, S. Review of Purely 4f and Mixed-Metal Nd-4f Single-Molecule Magnets Containing Only One Lanthanide Ion. *Coord. Chem. Rev.* **2014**, *276*, 1–33 DOI: 10.1016/j.ccr.2014.05.011.
- (7) Sañudo, E. C.; Rosado Piquer, L. Heterometallic 3d-4f Single-Molecule Magnets. *Dalton Trans.* **2015**, *44*, 8771–8780 DOI: 10.1039/C5DT00549C.
- (8) Liu, J.-L.; Chen, Y.-C.; Guo, F.-S.; Tong, M.-L. Recent Advances in the Design of Magnetic Molecules for Use as Cryogenic Magnetic Coolants. *Coord. Chem. Rev.* **2014**, *281*, 26–49 DOI: 10.1016/j.ccr.2014.08.013.
- (9) Yang, X.; Li, Z.; Wang, S.; Huang, S.; Schipper, D.; Jones, R. A. Self-Assembly of NIR Luminescent 30-Metal Drum-like and 12-Metal Rectangular D-F Nanoclusters with Long-Chain Schiff Base Ligands. *Chem. Commun.* **2014**, *50*, 15569–15572 DOI: 10.1039/c4cc07174c.
- (10) Burrow, C. E.; Burchell, T. J.; Lin, P.-H.; Habib, F.; Wernsdorfer, W.; Clérac, R.; Murugesu, M. Salen-Based [Zn₂Ln₃] Complexes with Fluorescence and Single-Molecule-Magnet Properties. *Inorg. Chem.* **2009**, *48*, 8051–8053 DOI: 10.1021/ic9007944.
- (11) Jankolovits, J.; Andolina, C. M.; Kampf, J. W.; Raymond, K. N.; Pecoraro, V. L. Assembly of near-Infrared Luminescent Lanthanide Host(host-Guest) Complexes with a Metallocrown Sandwich Motif. *Angew. Chem. Int. Ed.* **2011**, *50*, 9660–9664 DOI: 10.1002/anie.201103851.
- (12) Alexandropoulos, D. I.; Fournet, A.; Cunha-Silva, L.; Mowson, A. M.; Bekiari, V.; Christou,

- G.; Stamatatos, T. C. Fluorescent Naphthalene Diols as Bridging Ligands in Ln(III) Cluster Chemistry: Synthetic, Structural, Magnetic, and Photophysical Characterization of Ln(III)₈ "Christmas Stars." *Inorg. Chem.* **2014**, *53*, 5420–5422 DOI: 10.1021/ic500806n.
- (13) Rodríguez-Cortinas, R.; Avecilla, F.; Platas-Iglesias, C.; Imbert, D.; Bünzli, J.-C. G.; de Blas, A.; Rodríguez-Blas, T. Structural and Photophysical Properties of Heterobimetallic 4f-Zn Iminophenolate Cryptates. *Inorg. Chem.* **2002**, *41*, 5336–5349 DOI: 10.1021/ic025587s.
 - (14) Maayan, G.; Christou, G. "Old" Clusters with New Function: Oxidation Catalysis by High Oxidation State Manganese and Cerium/manganese Clusters Using O₂ Gas. *Inorg. Chem.* **2011**, *50*, 7015–7021 DOI: 10.1021/ic200393y.
 - (15) Griffiths, K.; Gallop, C. W. D.; Abdul-Sada, A.; Vargas, A.; Navarro, O.; Kostakis, G. E. Heteronuclear 3 d/Dy(III) Coordination Clusters as Catalysts in a Domino Reaction. *Chem. Eur. J.* **2015**, *21*, 6358–6361 DOI: 10.1002/chem.201500505.
 - (16) Evangelisti, F.; More, R.; Hodel, F.; Luber, S.; Patzke, G. R. 3d-4f {Co(II)₃Ln(OR)₄} Cubanes as Bio-Inspired Water Oxidation Catalysts. *J. Am. Chem. Soc.* **2015**, *137*, 11076–11084 DOI: 10.1021/jacs.5b05831.
 - (17) Griffiths, K.; Kumar, P.; Akien, G.; Chilton, N. F.; Abdul-Sada, A.; Tizzard, G. J.; Coles, S.; Kostakis, G. E. Tetranuclear Zn/4f Coordination Clusters as Highly Efficient Catalysts for Friedel Crafts Alkylation. *Chem. Commun.* **2016**, *52*, 7866–7869 DOI: 10.1039/C6CC03608B.
 - (18) Griffiths, K.; Kumar, P.; Mattock, J. D.; Abdul-Sada, A.; Pitak, M. B.; Coles, S. J.; Navarro, O.; Vargas, A.; Kostakis, G. E. Efficient NiII₂LnIII₂ Electrocyclization Catalysts for the Synthesis of Trans-4,5-Diaminocyclopent-2-Enones from 2-Furaldehyde and Primary or Secondary Amines. *Inorg. Chem.* **2016**, *55*, 6988–6994.
 - (19) Brewer, M.; Lee, J.; Brennan, J. G. Heterometallic Eu/M(II) Benzenethiolates (M = Zn, Cd, Hg): Synthesis, Structure, and Thermolysis Chemistry. *Inorg. Chem.* **1995**, *34*, 5919–5924 DOI: 10.1021/ic00127a033.
 - (20) Berardini, M.; Emge, T. J.; Brennan, J. G. Lanthanide-Group 12 Metal Chalcogenolates: A Versatile Class of Compounds. *Inorg. Chem.* **1995**, *34*, 5327–5334 DOI: 10.1021/ic00125a036.
 - (21) Daniele, S.; Hubert-Pfalzgraf, L. G.; Vaissermann, J. Reactions of Coordinated Alcohol as a Route to Mixed-Metal La–Zn Alkoxides: Molecular Structure of LaZn₃(μ-OBu)₆[N(SiMe₃)₂]₃. *Polyhedron* **1998**, *17*, 4249–4256 DOI: 10.1016/S0277-5387(98)00235-6.
 - (22) Cui, Y.; Qian, Y.-T.; Huang, J.-S. Synthesis, Characterization and X-Ray Structure of Three Types of Triply Crotonate-Bridged Heterometallic zinc(II)–lanthanide(III) Complexes. *Polyhedron* **2001**, *20*, 1795–1802 DOI: 10.1016/S0277-5387(01)00714-8.
 - (23) Upadhyay, A.; Singh, S. K.; Das, C.; Mondol, R.; Langley, S. K.; Murray, K. S.; Rajaraman, G.; Shanmugam, M. Enhancing the Effective Energy Barrier of a Dy(III) SMM Using a Bridged Diamagnetic Zn(II) Ion. *Chem. Commun.* **2014**, *50*, 8838–8841 DOI: 10.1039/C4CC02094D.
 - (24) Sakamoto, M.; Manseki, K.; Kawa, H. D-F Heteronuclear Complexes: Synthesis, Structures and Physicochemical Aspects. *Coord. Chem. Rev.* **2001**, *219–221*, 379–414 DOI: 10.1016/S0010-8545(01)00341-1.
 - (25) Abtab, S. M. T.; Majee, M. C.; Maity, M.; Titiš, J.; Boča, R.; Chaudhury, M. Tetranuclear Hetero-Metal [Co(II)₂Ln(III)₂] (Ln = Gd, Tb, Dy, Ho, La) Complexes Involving Carboxylato Bridges in a Rare μ₄-η(2):η(2) Mode: Synthesis, Crystal Structures, and Magnetic Properties. *Inorg. Chem.* **2014**, *53*, 1295–1306 DOI: 10.1021/ic401484d.

- (26) Long, J.; Rouquette, J.; Thibaud, J.-M.; Ferreira, R. A. S.; Carlos, L. D.; Donnadiou, B.; Vieru, V.; Chibotaru, L. F.; Konczewicz, L.; Haines, J.; Guari, Y.; Larionova, J. A High-Temperature Molecular Ferroelectric Zn/Dy Complex Exhibiting Single-Ion-Magnet Behavior and Lanthanide Luminescence. *Angew. Chem. Int. Ed.* **2015**, *54*, 2236–2240 DOI: 10.1002/anie.201410523.
- (27) Pasatoiu, T. D.; Tiseanu, C.; Madalan, A. M.; Jurca, B.; Duhayon, C.; Sutter, J. P.; Andruh, M. Study of the Luminescent and Magnetic Properties of a Series of Heterodinuclear [Zn(II)Ln(III)] Complexes. *Inorg. Chem.* **2011**, *50*, 5879–5889 DOI: 10.1021/ic200426w.
- (28) Brechin, E. K.; Piligkos, S.; Evangelisti, M.; Sethi, W.; Pedersen, K. S.; Lorusso, G.; Sørensen, M. A.; Nichol, G. S.; Sanz, S. Magnetic and Magnetocaloric Properties of an Unusual Family of Carbonate-Panelled [LnIII₆ZnII₂] Cages. *Dalton Trans.* **2015**, *44*, 10315–10320 DOI: 10.1039/C5DT01240F.
- (29) Jankolovits, J.; Kampf, J. W.; Pecoraro, V. L. Solvent Dependent Assembly of Lanthanide Metallocrowns Using Building Blocks with Incompatible Symmetry Preferences. *Inorg. Chem.* **2014**, *53*, 7534–7546 DOI: 10.1021/ic500832u.
- (30) Palacios, M. A.; Titos-Padilla, S.; Ruiz, J.; Herrera, J. M.; Pope, S. J. A.; Brechin, E. K.; Colacio, E. Bifunctional Zn(II)Ln(III) Dinuclear Complexes Combining Field Induced SMM Behavior and Luminescence: Enhanced NIR Lanthanide Emission by 9-Anthracene Carboxylate Bridging Ligands. *Inorg. Chem.* **2014**, *53*, 1465–1474 DOI: 10.1021/ic402597s.
- (31) Samanta, S. K.; Abtab, S. M. T.; Sardar, P. S.; Sanyal, S.; Chaudhury, M.; Ghosh, S. Role of Triplet States of Two Different Ligands in the Sensitized Emission of Ln III (Eu III, Tb III) in D-F Hybrid Tetranuclear Heterometal (Zn II₂Ln III₂, Cd II₂Ln III₂) Complexes. *Eur. J. Inorg. Chem.* **2014**, *2014*, 3101–3113 DOI: 10.1002/ejic.201402274.
- (32) Ruiz, J.; Lorusso, G.; Evangelisti, M.; Brechin, E. K.; Pope, S. J. A.; Colacio, E. Closely-Related Zn(II)₂Ln(III)₂ Complexes (Ln(III) = Gd, Yb) with Either Magnetic Refrigerant or Luminescent Single-Molecule Magnet Properties. *Inorg. Chem.* **2014**, *53*, 3586–3594 DOI: 10.1021/ic403097s.
- (33) Zheng, Z.-P.; Ou, Y.-J.; Hong, X.-J.; Wei, L.-M.; Wan, L.-T.; Zhou, W.-H.; Zhan, Q.-G.; Cai, Y.-P. Anion-Dependent Assembly of Four Sensitized near-Infrared Luminescent Heteronuclear Zn(II)-Yb(III) Schiff Base Complexes from a Trinuclear Zn(II) Complex. *Inorg. Chem.* **2014**, *53*, 9625–9632 DOI: 10.1021/ic501118b.
- (34) Zhang, P.; Zhang, L.; Lin, S.-Y.; Tang, J. Tetranuclear [MDy]₂ Compounds and Their Dinuclear [MDy] (M = Zn/Cu) Building Units: Their Assembly, Structures, and Magnetic Properties. *Inorg. Chem.* **2013**, *52*, 6595–6602 DOI: 10.1021/ic400620j.
- (35) Zhang, B.; Zheng, X.; Su, H.; Zhu, Y.; Du, C.; Song, M. Efficient Fixation of Atmospheric CO₂ as Carbonate by Lanthanide-Based Complex via Synergistic Effect of Zinc Ion. *Dalton Trans.* **2013**, *42*, 8571–8574 DOI: 10.1039/c3dt50230a.
- (36) Yu, W.-R.; Lee, G.-H.; Yang, E.-C. Systematic Studies of the Structures and Magnetic Properties for a Family of Cubane Complexes with the Formula: [M₂Ln₂] (Ln = Dy, Gd; M = Ni, Zn) and [Ni₂Y₂]. *Dalton Trans.* **2013**, *42*, 3941–3949 DOI: 10.1039/c2dt32688d.
- (37) Dinca, A. S.; Vallejo, J.; Shova, S.; Lloret, F.; Julve, M.; Andruh, M. Synthesis, Crystal Structure and Magnetic Properties of a New [ZnII₆DyIII₆] Dodecanuclear Motif. *Polyhedron* **2013**, *65*, 238–243 DOI: 10.1016/j.poly.2013.08.049.
- (38) Jankolovits, J.; Kampf, J. W.; Pecoraro, V. L. Insight into the Structural Versatility of the Ln(III)[15-Metallacrown-5] Platform by Comparing Analogs with Ni(II), Cu(II), and Zn(II) Ring Ions. *Polyhedron* **2013**, *52*, 491–499 DOI: 10.1016/j.poly.2012.08.046.
- (39) Ehama, K.; Ohmichi, Y.; Sakamoto, S.; Fujinami, T.; Matsumoto, N.; Mochida, N.; Ishida, T.; Sunatsuki, Y.; Tsuchimoto, M.; Re, N. Synthesis, Structure, Luminescent, and Magnetic

Properties of Carbonato-Bridged Zn(II)₂Ln(III)₂ Complexes [(μ₄-CO₃)₂{Zn(II)L(n)Ln(III)(NO₃)₂}₂] (Ln(III) = Gd(III), Tb(III), Dy(III); L(1) = N,N'-bis(3-Methoxy-2-Oxybenzylidene)-1,3-Propanediaminato, L(2) = N. *Inorg. Chem.* **2013**, *52*, 12828–12841 DOI: 10.1021/ic4022273.

- (40) Abtab, S. M. T.; Maity, M.; Bhattacharya, K.; Sañudo, E. C.; Chaudhury, M. Syntheses, Structures, and Magnetic Properties of a Family of Tetranuclear Hydroxido-Bridged Ni(II)₂Ln(III)₂ (Ln = La, Gd, Tb, and Dy) Complexes: Display of Slow Magnetic Relaxation by the zinc(II)-dysprosium(III) Analogue. *Inorg. Chem.* **2012**, *51*, 10211–10221 DOI: 10.1021/ic301138r.
- (41) Titos-Padilla, S.; Ruiz, J.; Herrera, J. M.; Brechin, E. K.; Wersndorfer, W.; Lloret, F.; Colacio, E. Dilution-Triggered SMM Behavior under Zero Field in a Luminescent Zn₂Dy₂ Tetranuclear Complex Incorporating Carbonato-Bridging Ligands Derived from Atmospheric CO₂ Fixation. *Inorg. Chem.* **2013**, *52*, 9620–9626 DOI: 10.1021/ic401378k.
- (42) Hooper, T. N.; Schnack, J.; Piligkos, S.; Evangelisti, M.; Brechin, E. K. The Importance of Being Exchanged: [Gd(III)₄M(II)₈(OH)₈(L)₈(O₂CR)₈]₄⁺ Clusters for Magnetic Refrigeration. *Angew. Chem. Int. Ed.* **2012**, *51*, 4633–4636 DOI: 10.1002/anie.201200072.
- (43) Long, J.; Vallat, R.; Ferreira, R. A. S.; Carlos, L. D.; Almeida Paz, F. A.; Guari, Y.; Larionova, J. A Bifunctional Luminescent Single-Ion Magnet: Towards Correlation between Luminescence Studies and Magnetic Slow Relaxation Processes. *Chem. Commun.* **2012**, *48*, 9974–9976 DOI: 10.1039/c2cc35321k.
- (44) Feltham, H. L. C.; Lan, Y.; Klöwer, F.; Ungur, L.; Chibotaru, L. F.; Powell, A. K.; Brooker, S. A Non-Sandwiched Macrocyclic Monolanthanide Single-Molecule Magnet: The Key Role of Axiality. *Chem. Eur. J.* **2011**, *17*, 4362–4365 DOI: 10.1002/chem.201100438.
- (45) Meng, Z.-S.; Guo, F.-S.; Liu, J.-L.; Leng, J.-D.; Tong, M.-L. Heterometallic Cubane-like {M₂Ln₂} (M = Ni, Zn; Ln = Gd, Dy) and {Ni₂Y₂} Aggregates. Synthesis, Structures and Magnetic Properties. *Dalton Trans.* **2012**, *41*, 2320–2329 DOI: 10.1039/c1dt10869g.
- (46) Oyarzabal, I.; Ruiz, J.; Ruiz, E.; Aravena, D.; Seco, J. M.; Colacio, E. Increasing the Effective Energy Barrier Promoted by the Change of a Counteranion in a Zn-Dy-Zn SMM: Slow Relaxation via the Second Excited State. *Chem. Commun.* **2015**, *51*, 12353–12356 DOI: 10.1039/c5cc04495b.
- (47) Lo, W.-K.; Wong, W.-K.; Wong, W.-Y.; Guo, J.; Yeung, K.-T.; Cheng, Y.-K.; Yang, X.; Jones, R. A. Heterobimetallic Zn(II)-Ln(III) Phenylene-Bridged Schiff Base Complexes, Computational Studies, and Evidence for Singlet Energy Transfer as the Main Pathway in the Sensitization of near-Infrared Nd³⁺ Luminescence. *Inorg. Chem.* **2006**, *45*, 9315–9325 DOI: 10.1021/ic0610177.
- (48) Andruh, M. The Exceptionally Rich Coordination Chemistry Generated by Schiff-Base Ligands Derived from O-Vanillin. *Dalton Trans.* **2015**, *44*, 16633–16653 DOI: 10.1039/C5DT02661J.
- (49) Chojnacki, J.; Oleksyn, B.; Zukowska, E. Prototype Ligand with Uranium. *Rocz. Chem.* **1971**, *45*, 487.
- (50) Mondal, K. C.; Kostakis, G. E.; Lan, Y.; Wersndorfer, W.; Anson, C. E.; Powell, A. K. Defect-Dicubane Ni₂Ln₂ (Ln = Dy, Tb) Single Molecule Magnets. *Inorg. Chem.* **2011**, *50*, 11604–11611 DOI: 10.1021/ic2015397.
- (51) Mondal, K. C.; Sundt, A.; Lan, Y.; Kostakis, G. E.; Waldmann, O.; Ungur, L.; Chibotaru, L. F.; Anson, C. E.; Powell, A. K. Coexistence of Distinct Single-Ion and Exchange-Based Mechanisms for Blocking of Magnetization in a Co(II)₂Dy(III)₂ Single-Molecule Magnet. *Angew. Chem. Int. Ed.* **2012**, *51*, 7550–7554 DOI: 10.1002/anie.201201478.
- (52) Ke, H.; Zhao, L.; Guo, Y.; Tang, J. Syntheses, Structures, and Magnetic Analyses of a

Family of Heterometallic Hexanuclear [Ni₄M₂] (M = Gd, Dy, Y) Compounds: Observation of Slow Magnetic Relaxation in the Dy(III) Derivative. *Inorg. Chem.* **2012**, *51*, 2699–2705 DOI: 10.1021/ic202699k.

- (53) Nemec, I.; Machata, M.; Herchel, R.; Boča, R.; Trávníček, Z. A New Family of Fe₂Ln Complexes Built from Mononuclear Anionic Schiff Base Subunits. *Dalton Trans.* **2012**, *41*, 14603–14610 DOI: 10.1039/c2dt31809a.
- (54) Ke, H.; Zhu, W.; Zhang, S.; Xie, G.; Chen, S. A New Family of Heterometallic Tetranuclear [Mn^{III}₂Ln^{III}₂] (Ln = Eu, Gd, Tb, Dy) Isostructural Clusters: Syntheses, Crystal Structures and Magnetic Properties. *Polyhedron* **2015**, *87*, 109–116 DOI: 10.1016/j.poly.2014.10.030.
- (55) Ke, H.; Zhang, S.; Zhu, W.; Xie, G.; Chen, S. Synthesis, Structures and Magnetic Properties of Four Dodecanuclear Ni₈RE₄ (RE = Gd, Dy, Y) Clusters Trapping Four μ_5 -Bridged Carbonate Anions. *J. Coord. Chem.* **2015**, *68*, 808–822 DOI: 10.1080/00958972.2015.1004326.
- (56) Kumar, P.; Lymperopoulou, S.; Griffiths, K.; Sampani, S. I.; Kostakis, G. E. Highly Efficient Tetranuclear Zn^{II}₂Ln^{III}₂ Catalysts for the Friedel – Crafts Alkylation of Indoles and Nitrostyrenes. *Catalysts* **2016**, *6*, 140.
- (57) Kumar, P.; Griffiths, K.; Lymperopoulou, S.; Kostakis, G. E.; Kostakis, G. E. Tetranuclear Zn₂Ln₂ Coordination Clusters as Catalysts in the Petasis Borono-Mannich Multicomponent Reaction. *RSC Adv.* **2016**, *6*, 79180–79184 DOI: 10.1039/C6RA17209A.
- (58) Yang, X.; Schipper, D.; Liao, A.; Stanley, J. M.; Jones, R. A.; Holliday, B. J. Anion Dependent Self-Assembly of Luminescent Zn-Ln (Eu and Tb) Salen Complexes. *Polyhedron* **2013**, *52*, 165–169 DOI: 10.1016/j.poly.2012.10.014.
- (59) Griffiths, K.; Dokorou, V. N.; Spencer, J.; Abdul-Sada, A.; Vargas, A.; Kostakis, G. E. Isoskeletal Schiff Base Polynuclear Coordination Clusters: Synthetic and Theoretical Aspects. *CrystEngComm* **2016**, *18*, 704–713 DOI: 10.1039/C5CE02109J.
- (60) Palopoli, C.; González-Sierra, M.; Robles, G.; Dahan, F.; Tuchagues, J.-P.; Signorella, S. Synthesis and Characterisation of Dimanganese(III) Complexes of 1,5-bis(X-Salicylidenamino)pentan-3-ol (X = 3- or 5-Methoxy) and Their Catalytic Activity towards Hydrogen Peroxide Disproportionation. *J. Chem. Soc. Dalton Trans.* **2002**, 3813–3819 DOI: 10.1039/b204566d.
- (61) Coles, S. J.; Gale, P. A. Changing and Challenging Times for Service Crystallography. *Chem. Sci.* **2012**, *3*, 683–689 DOI: 10.1039/c2sc00955b.
- (62) Sheldrick, G. M. Crystal Structure Refinement with SHELXL. *Acta Crystallogr. Sect. C Struct. Chem.* **2015**, *71*, 3–8 DOI: 10.1107/S2053229614024218.
- (63) Spek, A. L. Single-Crystal Structure Validation with the Program PLATON. *J. Appl. Crystallogr.* **2003**, *36*, 7–13 DOI: 10.1107/S0021889802022112.
- (64) Dolomanov, O. V.; Bourhis, L. J.; Gildea, R. J.; Howard, J. A. K.; Puschmann, H. OLEX2 : A Complete Structure Solution, Refinement and Analysis Program. *J. Appl. Crystallogr.* **2009**, *42*, 339–341 DOI: 10.1107/S0021889808042726.
- (65) Farrugia, L. J. WinGX and ORTEP for Windows : An Update. *J. Appl. Crystallogr.* **2012**, *45*, 849–854 DOI: 10.1107/S0021889812029111.
- (66) Macrae, C. F.; Edgington, P. R.; McCabe, P.; Pidcock, E.; Shields, G. P.; Taylor, R.; Towler, M.; Van De Streek, J. Mercury: Visualization and Analysis of Crystal Structures. *J. Appl. Crystallogr.* **2006**, *39*, 453–457 DOI: 10.1107/S002188980600731X.
- (67) King, P.; Clerac, R.; Wernsdorfer, W.; Anson, C. E.; Powell, A. K. Synthesis and Magnetism of Oxygen-Bridged Tetranuclear Defect Dicubane Co(II) and Ni(II) Clusters. *Dalton Trans.* **2004**, 2670–2676 DOI: 10.1039/B405881J.

- (68) M. Llunell, D. Casanova, J. Cirera, P. Alemany, S. A. SHAPE. *SHAPE version 2.0*. **2010**, Barcelona.
- (69) Kostakis, G. E.; Powell, A. K. An Approach to Describing the Topology of Polynuclear Clusters. *Coord. Chem. Rev.* **2009**, *253*, 2686–2697 DOI: 10.1016/j.ccr.2009.05.002.
- (70) Kostakis, G. E.; Blatov, V. A.; Proserpio, D. M. A Method for Topological Analysis of High Nuclearity Coordination Clusters and Its Application to Mn Coordination Compounds. *Dalton Trans.* **2012**, *41*, 4634–4640 DOI: 10.1039/c2dt12263d.
- (71) Allen, F. H. The Cambridge Structural Database: A Quarter of a Million Crystal Structures and Rising. *Acta Crystallogr. Sect. B-Structural Sci.* **2002**, *58*, 380–388 DOI: 10.1107/s0108768102003890.
- (72) Chen, P.; Chen, H.; Yan, P.; Wang, Y.; Li, G. Effect of Lanthanide Contraction and Rigid Ligand on the Structure of Salen-Type Lanthanide Complexes. *CrystEngComm* **2011**, *13*, 6237–6242 DOI: 10.1039/c1ce05501a.
- (73) Addison, A. W.; Rao, T. N.; Reedijk, J.; Vanriijn, J.; Verschoor, G. C. SYNTHESIS, STRUCTURE, AND SPECTROSCOPIC PROPERTIES OF COPPER(II) COMPOUNDS CONTAINING NITROGEN SULFUR DONOR LIGANDS - THE CRYSTAL AND MOLECULAR-STRUCTURE OF AQUA 1,7-BIS(N-METHYLBENZIMIDAZOL-2'-YL)-2,6-DITHIAHEPTANE COPPER(II) PERCHLORATE. *J. Chem. Soc. Trans.* **1984**, 1349–1356 DOI: 10.1039/dt9840001349.
- (74) Griffiths, K.; Novitchi, G.; Kostakis, G. E. Synthesis, Characterization, Magnetic Properties, and Topological Aspects of Isoskeletal Heterometallic Hexanuclear CoII4LnIII2 Coordination Clusters Possessing 2,3,4M6-1 Topology. *Eur. J. Inorg. Chem.* **2016**, *2016*, 2750–2756 DOI: 10.1002/ejic.201600078.
- (75) Chilton, N. F.; Langley, S. K.; Moubaraki, B.; Soncini, A.; Batten, S. R.; Murray, K. S. Single Molecule Magnetism in a Family of Mononuclear [Small Beta]-Diketonate Lanthanide(III) Complexes: Rationalization of Magnetic Anisotropy in Complexes of Low Symmetry. *Chem. Sci.* **2013**, *4*, 1719–1730 DOI: 10.1039/C3SC22300K.
- (76) Sievers, J. Asphericity of 4f-Shells in Their Hund's Rule Ground States. *Zeitschrift für Phys. B Condens. Matter* **1982**, *45*, 289–296 DOI: 10.1007/BF01321865.
- (77) Rinehart, J. D.; Long, J. R. Exploiting Single-Ion Anisotropy in the Design of F-Element Single-Molecule Magnets. *Chem. Sci.* **2011**, *2*, 2078–2085 DOI: 10.1039/C1SC00513H.
- (78) Chilton, N. F.; Collison, D.; McInnes, E. J. L.; Winpenny, R. E. P.; Soncini, A. An Electrostatic Model for the Determination of Magnetic Anisotropy in Dysprosium Complexes. *Nat. Commun.* **2013**, *4*, 2551 DOI: 10.1038/ncomms3551.
- (79) Zhang, L.; Zhao, L.; Zhang, P.; Wang, C.; Yuan, S.-W.; Tang, J. Nanoscale {Ln(III)24Zn(II)6} Triangular Metalloring with Magnetic Refrigerant, Slow Magnetic Relaxation, and Fluorescent Properties. *Inorg. Chem.* **2015**, *54*, 11535–11541 DOI: 10.1021/acs.inorgchem.5b02215.
- (80) Stavgianoudaki, N.; Siczek, M.; Lis, T.; Inglis, R.; Milios, C. J. A Triacontanuclear [Zn 12 Dy 18] Cluster: A Ring of [Dy 4] Cubes. *Chem. Commun.* **2016**, *52*, 343–345 DOI: 10.1039/C5CC07243C.
- (81) Shiga, T.; Hoshino, N.; Nakano, M.; Nojiri, H.; Oshio, H. Syntheses, Structures, and Magnetic Properties of Manganese-Lanthanide Hexanuclear Complexes. *Inorg. Chim. Acta* **2008**, *361*, 4113–4117 DOI: 10.1016/j.ica.2008.03.096.
- (82) Mereacre, V.; Ako, A.; Akhtar, M.; Lindemann, A.; Anson, C.; Powell, A. Homo- and Heterovalent Polynuclear Cerium and Cerium/Manganese Aggregates. *Helv. Chim. Acta* **2009**, *92*, 2507–2524 DOI: 10.1002/hlca.200900192.

- (83) Liu, J.; Ma, C.; Chen, H.; Hu, M.; Wen, H.; Cui, H.; Song, X.; Chen, C. Syntheses, Structures and Magnetic Properties of a Family of Heterometallic [Mn(II)₂Mn(III)₂Ln(III)₂] Clusters. *Dalton Trans.* **2013**, 42, 2423–2430 DOI: 10.1039/c2dt32269b.
- (84) Jhan, S.-Y.; Huang, S.-H.; Yang, C.-I.; Tsai, H.-L. Structure and Magnetic Properties of a 3d–4f CoIII₂DyIII₄ Cluster. *Polyhedron* **2013**, 66, 222–227.
- (85) Feuersenger, J.; Prodius, D.; Mereacre, V.; Clérac, R.; Anson, C. E.; Powell, A. K. Synthesis, Structure and Magnetic Properties of Hexanuclear CoIII–LnIII Clusters. *Polyhedron* **2013**, 66, 257–263.
- (86) Zhao, L.; Wu, J.; Ke, H.; Tang, J. Family of Defect-Dicubane Ni₄Ln₂ (Ln = Gd, Tb, Dy, Ho) and Ni₄Y₂ Complexes: Rare Tb(III) and Ho(III) Examples Showing SMM Behavior. *Inorg. Chem.* **2014**, 53, 3519–3525 DOI: 10.1021/ic402973g.
- (87) Tian, C.-B.; Yuan, D.-Q.; Han, Y.-H.; Li, Z.-H.; Lin, P.; Du, S.-W. Synthesis, Structures, and Magnetic Properties of a Series of New Heterometallic Hexanuclear Co₂Ln₄ (Ln = Eu, Gd, Tb and Dy) Clusters. *Inorg. Chem. Front.* **2014**, 1, 695–704 DOI: 10.1039/C4QI00116H.
- (88) Chen, S.; Mereacre, V.; Prodius, D.; Kostakis, G. E.; Powell, A. K. Developing a “Highway Code” To Steer the Structural and Electronic Properties of FeIII/DyIII Coordination Clusters. *Inorg. Chem.* **2015**, 54, 3218–3227 DOI: 10.1021/ic502809y.
- (89) Chakraborty, A.; Bag, P.; Goura, J.; Bar, A. K.; Sutter, J.-P.; Chandrasekhar, V. Chair-Shaped Mn^{II}₂Ln^{III}₄ (Ln = Gd, Tb, Dy, Ho) Heterometallic Complexes Assembled from a Tricompartamental Aminobenzohydrazide Ligand. *Cryst. Growth Des.* **2015**, 15, 848–857 DOI: 10.1021/cg501640y.
- (90) Oki, A. R.; Zhang, H. M.; Hosmane, N. S.; Ro, H. Y.; Hatfield, W. E. Trinuclear, Mixed-Valence, Zwitterionic, and Sandwiched Manganacarborane - a Novel Butterfly Cluster. *J. Am. Chem. Soc.* **1991**, 113, 8531–8532.
- (91) Xie, Y. S.; Liu, Q. L.; Jiang, H.; Ni, J. Novel Complexes of Ligands Containing Phenol and Alcohol Groups: From Polynuclear Cluster, 1D Coordination Polymer to 2D Supramolecular Assemblies. *Eur. J. Inorg. Chem.* **2003**, 4010–4016 DOI: 10.1002/ejic.200300384.
- (92) Yamamura, M.; Miyazaki, H.; Iida, M.; Akine, S.; Nabeshima, T. Nuclearity Control of a Trisaloph Zinc Cluster Complex Dependent on Minute Structural Differences in the Bridging Anions. *Inorg. Chem.* **2011**, 50, 5315–5317 DOI: 10.1021/ic2002833.
- (93) Akine, S.; Sunaga, S.; Taniguchi, T.; Miyazaki, H.; Nabeshima, T. Core / Shell Oligometallic Template Synthesis of Macrocyclic Hexaoxime. *Inorg. Chem.* **2007**, 46, 2959–2961.
- (94) Rinck, J.; Lan, Y.; Anson, C. E.; Powell, A. K. Coordination Cluster Nuclearity Decreases with Decreasing Rare Earth Ionic Radius in 1:1 Cr/Ln N-Butyldiethanolamine Compounds: A Journey across the Lanthanide Series from Cr₄III₄La₄–Cr₄IIITb₄ via Cr₃IIIDy₃ and Cr₃IIIHo₃ to Cr₂IIIEr₂–Cr₂IIILu₂. *Inorg. Chem.* **2015**, 54, 3107–3117 DOI: 10.1021/ic502930p.
- (95) Sheikh, J. A.; Goswami, S.; Konar, S. Modulating the Magnetic Properties by Structural Modification in a Family of Co–Ln (Ln = Gd, Dy) Molecular Aggregates. *Dalton Trans.* **2014**, 43, 14577–14585 DOI: 10.1039/c4dt01791a.
- (96) Goura, J.; Guillaume, R.; Rivière, E.; Chandrasekhar, V. Hexanuclear, Heterometallic, Ni₃Ln₃ Complexes Possessing O-Capped Homo- and Heterometallic Structural Subunits: SMM Behavior of the Dysprosium Analogue. *Inorg. Chem.* **2014**, 53, 7815–7823 DOI: 10.1021/ic403090z.
- (97) Feng, H.; Zhang, Z.; Feng, W.; Su, P.; Lü, X.; Fan, D.; Wong, W.-K.; Jones, R. A.; Su, C. Mixed Anion-Induced Salen-Based Zn₂Ln₃ (Ln=Nd, Yb or Er) Complexes with near-Infrared (NIR) Luminescent Properties. *Inorg. Chem. Commun.* **2014**, 43, 151–154 DOI:

10.1016/j.inoche.2014.02.034.

- (98) Yang, X. P.; Jones, R. A.; Lynch, V.; Oye, M.; Holmes, A. L. Synthesis and near Infrared Luminescence of a Tetrametallic Zn₂Yb₂ Architecture from a Trinuclear Zn₃L₂ Schiff Base Complex. *Dalton Trans.* **2005**, 849–851 DOI: 10.1039/b416695g.
- (99) Yang, X.; Jones, R. a.; Huang, S. Luminescent 4f and D-4f Polynuclear Complexes and Coordination Polymers with Flexible Salen-Type Ligands. *Coord. Chem. Rev.* **2014**, 273–274, 63–75 DOI: 10.1016/j.ccr.2013.11.012.
- (100) Samanta, S. K.; Abtab, S. M. T.; Sardar, P. S.; Sanyal, S.; Chaudhury, M.; Ghosh, S. Role of Triplet States of Two Different Ligands in the Sensitized Emission of Ln(III) (Eu(III), Tb(III)) in D-F Hybrid Tetranuclear Heterometal (Zn(II)₂Ln(III)₂, Cd(II)₂Ln(III)₂) Complexes. *Eur. J. Inorg. Chem.* **2014**, 3101–3113 DOI: 10.1002/ejic.201402274.
- (101) Abtab, S. M. T.; Audhya, A.; Kundu, N.; Samanta, S. K.; Sardar, P. S.; Butcher, R. J.; Ghosh, S.; Chaudhury, M. Tetranuclear Homo- (Zn(II)₄ and Cd(II)₄) and Hetero-Metal (Zn(II)₂Tb(III)₂ and Cd(II)₂Tb(III)₂) Complexes with a Pair of Carboxylate Ligands in a Rare $\eta^2:\eta^2:\mu_4$ -Bridging Mode: Syntheses, Structures and Emission Properties. *Dalton Trans.* **2013**, 42, 1848–1861 DOI: 10.1039/c2dt30347g.
- (102) Meng, Z.-S.; Guo, F.-S.; Liu, J.-L.; Leng, J.-D.; Tong, M.-L. Heterometallic Cubane-like {M₂Ln₂} (M = Ni, Zn; Ln =, Gd, Dy) and {Ni₂Y₂} Aggregates. Synthesis, Structures and Magnetic Properties. *Dalt. Trans.* **2012**, 41, 2320–2329 DOI: 10.1039/C1DT10869G.
- (103) Akine, S.; Hotate, S.; Matsumoto, T.; Nabeshima, T. Spontaneous Enrichment of One-Handed Helices by Dissolution of Quasiracemic Crystals of a Tetranuclear Single Helical Complex. *Chem. Commun.* **2011**, 47, 2925–2927 DOI: 10.1039/c0cc04998k.
- (104) Akine, S.; Matsumoto, T.; Nabeshima, T. Spontaneous Formation of a Chiral Supramolecular Superhelix in the Crystalline State Using a Single-Stranded Tetranuclear Metallohelicite. *Chem. Commun.* **2008**, 4604–4606 DOI: 10.1039/b810426c.
- (105) Trivedi, E. R.; Eliseeva, S. V.; Jankolovits, J.; Olmstead, M. M.; Petoud, S.; Pecoraro, V. L. Highly Emitting near-Infrared Lanthanide “encapsulated Sandwich” metallacrown Complexes with Excitation Shifted toward Lower Energy. *J. Am. Chem. Soc.* **2014**, 136, 1526–1534 DOI: 10.1021/ja4113337.
- (106) Xiong, G.; Qin, X.-Y.; Shi, P.-F.; Hou, Y.-L.; Cui, J.-Z.; Zhao, B. New Strategy to Construct Single-Ion Magnets: A Unique Dy@Zn₆ Cluster Exhibiting Slow Magnetic Relaxation. *Chem. Commun.* **2014**, 50, 4255–4257 DOI: 10.1039/c3cc49342c.
- (107) Sopasis, G. J.; Orfanoudaki, M.; Zampas, P.; Philippidis, A.; Siczek, M.; Lis, T.; O’Brien, J. R.; Milios, C. J. 2-Aminoisobutyric Acid in Co(II) and Co(II)/Ln(III) Chemistry: Homometallic and Heterometallic Clusters. *Inorg. Chem.* **2012**, 51, 1170–1179 DOI: 10.1021/ic2024007.
- (108) Wei, T.; Zhao, S.; Bi, W.; Lü, X.; Hui, Y.; Song, J.; Wong, W.-K.; Jones, R. A. Co-Existence of Heterometallic Zn₂Er and ZnEr Arrayed Chromophores for the Sensitization of near-Infrared (NIR) Luminescence. *Inorg. Chem. Commun.* **2009**, 12, 1216–1219 DOI: 10.1016/j.inoche.2009.09.024.
- (109) Kornienko, A.; Huebner, L.; Freedman, D.; Emge, T. J.; Brennan, J. G. Lanthanide-Transition Metal Chalcogenido Cluster Materials. *Inorg. Chem.* **2003**, 42, 8476–8480 DOI: 10.1021/ic030204r.
- (110) Lü, X.; Bi, W.; Chai, W.; Song, J.; Meng, J.; Wong, W.-Y.; Wong, W.-K.; Yang, X.; Jones, R. A. Multinuclear NIR Luminescent 1,4-BDC Bridged Schiff-Base Complexes of Nd(III). *Polyhedron* **2009**, 28, 27–32 DOI: 10.1016/j.poly.2008.09.014.
- (111) Blatov, V. A.; Shevchenko, A. P.; Proserpio, D. M. Applied Topological Analysis of Crystal


Structures with the Program Package ToposPro. *Cryst. Growth Des.* **2014**, *14*, 3576–3586
DOI: 10.1021/cg500498k.

For Table of Contents Use Only

Four new families of polynuclear Zn-Ln coordination clusters. Synthetic, topological, magnetic and luminescent aspects.

Kieran Griffiths,^a Julia Mayans,^b Michael A. Shipman,^c Graham J. Tizzard,^d Simon J. Coles,^d Barry A. Blight,^c Albert Escuer,^b and George E Kostakis^{a,e,}*

TOC graphic



Synopsis

The employment of three structurally related Schiff bases with zinc and lanthanide salts under various reaction conditions, gave four families of compounds with robust and novel topologies. Synthetic aspects, topological analysis, magnetic studies and fluorescence studies are also discussed.